



Grade of resistance  
MAPEFLOOR FINISH 451

Test method ISO EN 438-2

Resistance to	Temperature test +23°C		
	2h	8h	24h
Xylene	5	5	4
Gasoline	5	5	5
Diesel oil	5	5	5
Brake fluid	5	5	4
Ethanol	5	5	5
Sodium Hydroxide (5% solution)	5	5	5
Ammonia (10% solution)	5	5	5
Bleach (10% solution)	5	5	5
Hydrochloric acid (10% solution)	3	3	3

**Legend :**

5= no visible change

4= slight change of gloss and/or color, only visible at certain viewing angles

3= moderate change of gloss and/or color

2= marked change of gloss and/or color

1= blistering and/or delamination