Chemical Resistance ISO 2812-1 MAPECOAT I62W

Chemical	*T °C*	1h	3h	6h	24h
Formalin 37%	23°C	0	0	0	0
Ammoniac 25%	23°C	0	0	0	0
Hydrogen peroxide 30%	23°C	1	2	5	5
Sulfuric acid 5%	23°C	3	4	4	5
Phophoric acid 30%	23°C	4	4	4	5
Peracetic acid 15%	23°C	5	5	5	5
Hydrochloric acid 5%	23°C	0	3	4	5
Isopropanol 100%	23°C	0	0	0	0
Sodium hydroxide 5%	23°C	0	0	0	0
Sodium hypochlorite 15%	23°C	0	0	0	0

0 = excellent
1 = very good
2 = good
3 = weak
4 = very weak
5 = none